

Testing Report

Colour Fastness	Test Items	Methods of Testing	Colour No.	1 SRE07	2 SRE24	3 SRE216	4 SRE14	5 SRE206	6 SRE37
		Ultraviolet carbon arc lamp light (Grade)	JIS L 0842	change in colour	>4	>4	>4	4	>4
	Washing and Laundering (Grade)	JIS L 0844 Method A-2	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	5 5	5 5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Perspiration (Grade)	JIS L 0848	acid	change in colour	4-5	4-5	4-5	4-5	4-5
			alkali	staining	5 5	5 5	4-5 4-5	4-5 4	4-5 4-5
	Rubbing (Grade)	JIS L 0849 Type II	dry	4-5	4-5	4-5	4	4-5	4-5
			wet	4-5	4-5	4-5	4-5	4-5	4-5
	Water (Grade)	JIS L 0846	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	5 5	5 5	4-5 4-5	4-5 4	4-5 4-5	4-5 4-5
	Dry cleaning (Grade)	JIS L 0860 Method A-1	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	5	5	4-5	4-5	4-5	4-5
	Bleeding (Grade)	DAIMARU Method I	staining	4-5	4-5	4-5	4-5	4-5	4-5

Colour Fastness	Test Items	Methods of Testing	Colour No.	7 SRE08	8 SRE15	9	10	11	12
		Ultraviolet carbon arc lamp light (Grade)	JIS L 0842	change in colour	>4	>4			
	Washing and Laundering (Grade)	JIS L 0844 Method A-2	change in colour	4-5	4-5				
			staining	4-5 4-5	4-5 4-5				
	Perspiration (Grade)	JIS L 0848	acid	change in colour	4-5	4-5			
			alkali	staining	4-5 4	4-5 4-5			
	Rubbing (Grade)	JIS L 0849 Type II	dry	(2-3)	4-5				
			wet	4	4-5				
	Water (Grade)	JIS L 0846	change in colour	4-5	4-5				
			staining	4-5 3-4	4-5 4-5				
	Dry cleaning (Grade)	JIS L 0860 Method A-1	change in colour	4-5	4-5				
			staining	4-5	4-5				
	Bleeding (Grade)	DAIMARU Method I	staining	4-5	4-5				

() Standard Unattained

SAMPLE	1 white	2 ivory	3 D.gray	4 black	5 dandelion	6 pink
	7 navy	8 aqua	9	10	11	12

Applicant	MONTELUCE/MARUYASU Corporation
	OKUBO
Article	1/60 PROOF PLUS ECO ALPHA-F0
	PQ0026
	8 Pieces
POLYESTER 100%	

Laboratory	THE JAPAN COTTON & STAPLE FIBER FABRIC INSPECTING INSTITUTE FOUNDATION	
	1-10-5, Komagome, Toshima-ku, Tokyo, Japan	
	TEL 03-3943-3174 FAX 03-3943-3183	
	Date	2025/4/1
	Test No.	TO-2502286-②
	Inspection House	Tokyo Test Center
Inspector	<i>S. Sato</i>	
Adjacent Fabric	Cotton / Nylon (multifiber fabric)	

Quantitative analysis of fibre mixtures (%)	
JIS L 1030-2	