

MARUYASU Corporation

3-21-5 RYOGOKU SUMIDAKU

TOKYO 130 0026 JAPAN

www.maruyasu-fil.co.jp

DATE: 2025/3/10

TECHNICAL DETAILS

YARN DESCRIPTION :	KARUNA		
COMPOSITION:	COTTON100%		
COUNT:	Nm.1/7.6	1 CONE:	1.0KG
TYPE OF DYEING:	Cone		
KNITTING:	5G-1PLY, 7G-1PLY		
STOCK SERVICE:	YES Minimum=1.0kg L/T:dyeing=3-4weeks		
OWN COLOR:	YES Minimum=3.0kg L/T:dyeing=3-4weeks ※NOTE: In case no stock of RW / spinning=6-8weeks+dyeing 3-4weeks		
FINISHING:	<ul style="list-style-type: none"> • Washing for 10 min with some softener (Water temp. 35°C) • Dewatering for 1min • Tumble dry for 3min • Press with a lot of steam ※ It is necessary to make specific trials in your own knits before starting production since the final result always depends on your equipment and the tension and stitch you choose.		
SPECIAL CARES:	<ol style="list-style-type: none"> 1. The cone should not be rewinded since not appropriate winding could jeopardize the yarn quality. 2. This item is dyed in cones and it may have the color differences between inside and outside of cones. We recommend to knit with more thread guides. We pay attention to this color difference, and we are not able to guarantee this problem if you have. 3. Striped or jacquard knitwear, dry cleaning is recommend. 		
CARE INSTRUCTION:	      		