

TECHNICAL DETAILS

YARN DESCRIPTION :	LICO		
COMPOSITION:	COTTON46% PAPER 42% SILK12%		
COUNT:	Nm.1/14	TYPE OF DYEING:	Hank
KNITTING:	7G-1PLY, 10G-1PLY		
STOCK SERVICE:	YES Minimum=1.0kg L/T:dyeing=3-4weeks		
OWN COLOR:	YES Minimum=3.0kg L/T:dyeing=3-4weeks ※NOTE: In case no stock of RW / spinning=6-8weeks+dyeing 3-4weeks		
FINISHING:	<ul style="list-style-type: none"> • Washing for 10 min with some softener (Water temp. 35°C) • Dewatering for 1min • Tumble dry for 3min • Press with a lot of steam. ※It is necessary to make specific trials in your own knits before starting production since the final result always depends on your equipment and the tension and stitch you choose.		
SPECIAL CARES:	<ol style="list-style-type: none"> 1. The cone should not be rewinded since not appropriate winding could jeopardize the yarn quality. 2. This yarn is dyed in hunks, and has the knots in composition, please knit with care to avoid the knots 3. Striped or jacquard knitwear, dry cleaning is recommend. 		

CAUTION WHEN KNITTING WITH PAPER:

Japanese paper material has low elasticity. For knitted structures that require more strain, (cables with large cross section, extreme tight or loose tension, sudden decrease in fully fashioning) may lead to yarn breakage or damage.

Please take into consideration this quality when designing. To maintain a stable tension and stable cone positioning, using a thread net will prevent yarn slip on the cone.

